

# CB12-400

DATASHEET - ROUTED & STRIP FOILED CHIPBOARD PANEL FOR JOISTS/BATTENS AT 400mm CENTRES


DS\_CB12-400\_01.0



Combination Panel (Pattern 6) CB12-400 (P5)-PAT6 CB12-400 (P6)-PAT6


CB12-400 (P7)-PAT6

#### **ROUTED PANEL CROSS SECTION**



- 1 Soft temper aluminium diffuser
- 2 12mm channel
- 3 P5, P6 or P7 chipboard

#### **APPLICATION CROSS SECTION**



- 1 Floor finish
- 2 Minimum 6mm flooring grade plywood
- 3 12mm pipe
- 4 Joisted or battened subfloor

## PRODUCT OVERVIEW

Independently tested structural underfloor heating panel which replaces the floor deck used in constructions on a joisted or battened floor and provides a high output as the pipe is as close to the floor finish as possible. Manufactured from P5, P6 or P7 tongued and grooved chipboard, the panels have pre-routed channels to accept 12mm continuous pipe (supplied by others) and are factory fitted with aluminium diffuser strips to provide improved performance and a means of detecting the pipe. The panels are laid on 400mm centre joists or battens in industry standard brick pattern and the pipe is installed by piercing through the soft temper aluminium diffuser strips. The flow and return pipework for each circuit drop into the joist space and are fed to and from the manifold as a continuous system beneath the floor level. The panels then require a minimum 6mm flooring grade Ply screwed and glued to complete the structural deck.

### **PRODUCT TECHNICAL DATA**

Material (Grades) P5 & P7 for humid conditions, P6 for dry conditions

Panel profile Tongued and grooved

Panel dimensions 2400 x 600mm

Thickness 22mm

Panel options Combination panel (P6)

Pipe centres 150mm
Pipe channels/external pipe diameter 12mm
100mm wide foil diffuser strips 50µm
Joist centres 400mm
Thermal conductivity 0.13W/mK

Hygiene Class (Formaldehyde EN120) E1 (≤ 8.0mg per 100g)

timoleon.eu.com

	Grade P5	Grade P6	Grade P7
Density	670 kg/m3	700 kg/m3	770 kg/m3
Bending Strength (EN310)	14 N/mm2	16 N/mm2	18.5 N/mm2
Integral Bond tensile strength (EN319)	0.40 N/mm2	0.40 N/mm2	0.65 N/mm2
Modules of elasticity in bending (EN310)	2150 N/mm2	2550 N/mm2	2900 N/mm2
Swelling in thickness 24 h immersion in water (EN317)	10%	15%	10%
Internal bond tensile strength after moisture stress test (EN321)	0.20 N/mm2		0.33 N/mm2
Swelling in thickness after humidity/moisture stress test (EN321)	11%		10%
Fire Class (EN 13501-1)	D	D	D

#### **MATERIAL CREDENTIALS**


- Structurally tested to EN 1195:1998 and EN 12872:2010 and assessed against the requirements of Class I of EN 12871:2013 (E). All tests passed and carried out by an accredited, external consultancy lab. Point Load results yielded a preliminary F<sub>maxest</sub> of 8.31 kN.
- · FSC Certified.
- CE Mark.
- · 100% recyclable.

#### **INSTALLATION GUIDANCE**

- 1. Store panels in a safe dry, weather tight area out of direct sunlight. All boards, must be stacked horizontally and raised off the ground and must not be exposed to moisture or high humidity.
- 2. Ensure all joists & battens are level & even, free from nails, debris etc before installation commences.
- 3. Lay panels perpendicular to the joists/ batten subfloor in a run ensuring the end of each panel falls on a joist/ batten centre line. Use the off-cut of each run to start the next run. Ensure that each row of panels has a group of return loops at each end.
- 4. Panels must be glued on both sides of all adjoining tongues & grooves and screwed and glued to the joists with appropriate PVA adhesive.
- 5. At the first panel of your circuit, drill a hole at a 20° angle in your first routed channel and feed your pipework (flow) into the floor void. Proceed to the floor below and feed the pipework through the void to the manifold location. Return to your coil of pipework and insert the pipe into the routed board channels piercing the aluminium diffuser strips as you go. At the end of your circuit, drill a second 20° hole to drop your pipework (return) and feed this back to the manifold from below. Continue for all circuits.
- 6. Pressure test each circuit on the system.
- 7. Bond & mechanically fix a minimum of 6mm flooring grade ply over the CB12 panel staggered and in the opposite direction to provide further rigidity to complete the structural deck ready to receive floor finish.

**Note:** If access is available to the floor void from below, steps 3 to 7 can be completed for the whole floor deck at once. If access is NOT available to the floor void from below, steps 3-7 will need to be completed room by room, starting at the room furthest from the manifold with the flow and return pipework fitted from above into the void.

## **DETAILS OF PANEL DESIGN OPTIONS**



Combination Panel (Pattern 6)

#### **PRODUCT TOLERANCE**

Panel

Length +/-2mm Width +/-2mm Thickness +/-0.5mm

Channel routed depth
12mm pipe -0/+0.3mm